

product name		Production location	
Wasserstrich Médoc		Spijk	
The most important base material for this type of facing brick is Westerwald clay, a natural white baking clay of the Westerwald region in the western part of Germany. Due to the use of the water-struck-technique the facing bricks sight will appear textured without sand coated surface.			
Colour			
Red brown with dark shades, textured without sand coated surface (Water-struck)			
Format			
Moulding method		Waterstruck	
WF: 208 x 98 x 50 mm DF: 216 x 103 x 67 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
		0620-CPR-76485	
Dimensions: tolerance category	T2		
Dimensions: range category	R1		
Active soluble salt	S2		
Average compressive strength	NPD	Tested to the bed face	
Normalised compressive strength	$\geq 30 \text{ N/mm}^2$	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm <sup>2</sup>	Value according EN998-2 Annex C	
Adhesive strength (mortar)	0,30 N/mm <sup>2</sup>	Value according EN998-2 Annex C	
Reaction to fire	A1	Category	
Water absorption	$\leq 7\% \text{ m/md}$		
Water vapour permeability	50/100		
Net dry density	1900 kg/m <sup>3</sup> (D1)		
Gross dry density	2000 kg/m <sup>3</sup> (D1)		
Equivalent thermal conductivity	$\leq 0,53 \text{ W/m.K}$	Value according EN1745, Annex A 50%	
Freeze/thaw resistance	F2		
Dangerous substances	NL-BSB	According Annex ZA.3	
Other Characteristics			
Initial rate of water absorption - Non-coated Brick	0,5 - 1,5 kg/m <sup>2</sup> .min (IW2)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption (kg/m <sup>2</sup> .min) - Coated Brick*	NPD	Value according EN771-1:2011 - 5.3.8	
Eq. Thermal Property 10, dry mass (90/90)	NPD		
Eq. Thermal Property 10, dry mass ( $\lambda_{U_i}$ )	NPD		
Eq. Thermal Property 10, dry mass ( $\lambda_{U_e}$ )	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> <li>- Store packs on a clean surface and cover them</li> <li>- Process from multiple packs at the same time</li> <li>- Follow the Vandersanden processing guidelines</li> </ul>		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.			