





product name		Production location
Handmade Old Chesterfield Nostalgie		Spouwen
The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.		
Colour		
a shade of yellow, pink and white to grey green with appearance of reclaimed brick		
Format		
Moulding method		Hand form
M50: 190 x 89 x 49 mm	Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1		
 0620-CPR-97882		
Dimensions: tolerance category	T2	
Dimensions: range category	R1	
Active soluble salt	S2	
Average compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Normalised compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	NPD	Value according EN998-2 Annex C
Adhesive strength (mortar)	NPD	Value according EN998-2 Annex C
Reaction to fire	A1	Category
Water absorption	$\leq 17\% \text{ m/md}$	
Water vapour permeability	5/10	
Net dry density	$1640 \text{ kg/m}^3 \text{ (D1)}$	
Gross dry density	$1530 \text{ kg/m}^3 \text{ (D1)}$	
Equivalent thermal conductivity	$\leq 0,55 \text{ W/m.K}$	Value according EN1745, Annex A 50%
Freeze/thaw resistance	F2	
Dangerous substances	NL-BSB	According Annex ZA.3
Other Characteristics		
Initial rate of water absorption - Non-coated Brick	$1,5 - 4,0 \text{ kg/m}^2 \cdot \text{min (IW3)}$	Value according EN771-1:2011 - 5.3.8
Initial rate of water absorption ($\text{kg/m}^2 \cdot \text{min}$) - Coated Brick*	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min (IW2)}$	Value according EN771-1:2011 - 5.3.8
Eq. Thermal Property 10, dry mass (90/90)	$0,60 \text{ W/m.K}$	
Eq. Thermal Property 10, dry mass (λ_{Ui})	$0,644 \text{ W/m.K}$	
Eq. Thermal Property 10, dry mass (λ_{Ue})	$1,27 \text{ W/m.K}$	
		
Storage & handling		Cutting
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.		

product name		Production location
Handmade Old Chesterfield Nostalgie		Lanklaar
The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.		
Colour		
a shade of yellow, pink and white to grey green with appearance of reclaimed brick		
Format		
Moulding method		Hand form
DF: 215 x 102 x 65 mm	Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1		
 0620-CPR-97884		
Dimensions: tolerance category	T2	
Dimensions: range category	R1	
Active soluble salt	S2	
Average compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Normalised compressive strength	NPD	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	$0,15 \text{ N/mm}^2$	Value according EN998-2 Annex C
Adhesive strength (mortar)	$0,30 \text{ N/mm}^2$	Value according EN998-2 Annex C
Reaction to fire	A1	Category
Water absorption	$\leq 17\% \text{ m/md}$	
Water vapour permeability	5/10	
Net dry density	$1640 \text{ kg/m}^3 \text{ (D1)}$	
Gross dry density	$1530 \text{ kg/m}^3 \text{ (D1)}$	
Equivalent thermal conductivity	$\leq 0,55 \text{ W/m.K}$	Value according EN1745, Annex A 50%
Freeze/thaw resistance	F2	
Dangerous substances	NL-BSB	According Annex ZA.3
Other Characteristics		
Initial rate of water absorption - Non-coated Brick	$1,5 - 4,0 \text{ kg/m}^2 \cdot \text{min} \text{ (IW3)}$	Value according EN771-1:2011 - 5.3.8
Initial rate of water absorption ($\text{kg/m}^2 \cdot \text{min}$) - Coated Brick*	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min} \text{ (IW2)}$	Value according EN771-1:2011 - 5.3.8
Eq. Thermal Property 10, dry mass (90/90)	$0,60 \text{ W/m.K}$	
Eq. Thermal Property 10, dry mass (λ_{Ui})	$0,644 \text{ W/m.K}$	
Eq. Thermal Property 10, dry mass (λ_{Ue})	$1,27 \text{ W/m.K}$	
		
Storage & handling		Cutting
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.		